

VT-4A2H

UL Approval: E214381 Version: Preliminary 1

Laminate/Prepreg

General Information

Ventec offers a series of Ceramic Filled thermally conductive Laminates and Prepregs for multilayer PCB applications requiring thermal dissipation. Laminates and prepregs provide ease of manufacture during ply-up. The prepreg provides higher thermal conductivity and flowability, which suits high power and heavy copper designs.

- > Thermal conductivity - 2.2W/mK, 8 times that of FR4
- > Tg 130°C & Td 380°C
- > Excellent thermal and insulation performance
- > MOT 105°C
- > Lead-free assembly compatible
- > ROHS & WEEE compliant

Application

- > Power Conversion
- > PDP, LED, Regulator for TV, Monitor Drives
- > Rectifier, Power supply
- > Automotive Electronics
- > Hybrid Multilayer Constructions
- > Other designs with thermal management requirements

Storage Condition & Shelf Life

		Prepreg		Laminate
Storage Condition	Temperature	< 23°C (73°F)	< 5°C (41°F)	Room
	Relative humidity	< 55%	/	/
Shelf Life		3 months	6 months	24 months

The Prepreg exceeding shelf life should be retested.

CORPORATE HEADQUARTERS

Ventec Electronics Co. Ltd.
308 TaiShan Rd,
New District Suzhou,
Jiangsu, P.R. China 215129
T: +86 512-68091810
Email: sales@ventec.com.cn

EMEA REGIONAL HEADQUARTERS

Ventec Europe
Unit 1 Trojan Business Centre,
Tachbrook Park Estate,
Leamington-Spa, CV34 6RH, UK
T: +44 1926-889822
Email: sales@ventec-europe.com

AMERICAS REGIONAL HEADQUARTERS

Ventec USA
700 Lee St., Elk Grove Village,
Illinois, IL 60007,
United States of America
T: +1 630-4221627
Email: saleseast@ventec-usa.com

www.ventec laminates.com

VT-4A2H

Laminate/Prepreg

UL Approval: E214381 Version: Preliminary1

Laminate Properties

Properties	Test Method	Units	Specification	Typical Value
Thermal Properties				
Tg	IPC-TM-650 2.4.25	°C	90 minimum	130
Td	ASTM D3850	°C	340 minimum	380
T260	IPC-TM-650 2.4.24.1	Minute	30 minimum	>60
T288	IPC-TM-650 2.4.24.1	Minute	15 minimum	>30
Thermal Stress @ 288°C	IPC-TM-650 2.4.13.1	Second	10 minimum	>600
Z-axis CTE	Before Tg	IPC-TM-650 2.4.24	ppm/°C	60 maximum
	After Tg	IPC-TM-650 2.4.24	ppm/°C	300 maximum
	Total Expansion (50-260°C)	IPC-TM-650 2.4.24	%	3.0 maximum
MOT	UL 746B	°C	-	105
Electrical Properties				
DK (RC 50%)	@ 1GHz	IPC-TM-650 2.5.5.9	-	7 maximum
DF (RC 50%)	@ 1GHz	IPC-TM-650 2.5.5.9	-	0.035 maximum
Volume Resistivity	After Moisture Resistance	IPC-TM-650 2.5.17.1	MΩ-cm	1.0E+4 minimum
	E-24/125	IPC-TM-650 2.5.17.1	MΩ-cm	1.0E+3 minimum
Surface Resistivity	After Moisture Resistance	IPC-TM-650 2.5.17.1	MΩ	1.0E+4 minimum
	E-24/125	IPC-TM-650 2.5.17.1	MΩ	1.0E+3 minimum
Electrical Strength		IPC-TM-650 2.5.6.2	Volt/mil (KV/mm)	762 (30) minimum
Dielectric Breakdown		IPC-TM-650 2.5.6	KV	40 minimum
Comparative Tracking Index (CTI)		ASTM D3638	Rating (Volt)	-
Mechanical Properties				
Peel Strength (1oz)	As received	IPC-TM-650 2.4.8	lb/in (N/mm)	6 (1.05)
	After thermal stress	IPC-TM-650 2.4.8	lb/in (N/mm)	6 (1.05) minimum
Physical Properties				
Moisture Absorption		IPC-TM-650 2.6.2.1	%	0.5 maximum
Flammability		UL-94	Rating	-
Thermal Conductivity	Z axis	ISO22007-2	W/mK	-
	X, Y axis			-

Note: All test data provided are typical values and not intended to be specification values.

CORPORATE HEADQUARTERS

Ventec Electronics Co. Ltd.
 308 TaiShan Rd,
 New District Suzhou,
 Jiangsu, P.R. China 215129
 T: +86 512-68091810
 Email: sales@ventec.com.cn

EMEA REGIONAL HEADQUARTERS

Ventec Europe
 Unit 1 Trojan Business Centre,
 Tachbrook Park Estate,
 Leamington-Spa, CV34 6RH, UK
 T: +44 1926-889822
 Email: sales@ventec-europe.com

AMERICAS REGIONAL HEADQUARTERS

Ventec USA
 700 Lee St., Elk Grove Village,
 Illinois, IL 60007,
 United States of America
 T: +1 630-4221627
 Email: saleseast@ventec-usa.com

www.ventec laminates.com

VT-4A2H

UL Approval: E214381 Version: Preliminary 1

Laminate/Prepreg

Availability

Laminate

Item	Availability
Copper Foil	Hoz, 1oz, 2oz, 3oz
Dielectric	.003" (80um), .004" (100um), .006" (150um), .008" (200um)
Standard Size	37"*49", 41"*49", 43"*49", and panels could be cut from above sizes.

Prepreg

Glass Fabric	Press Thickness (um)
106*	80
106	125
106	150

Remark: 106* has limited ability of resin filling. Please contact Ventec Technical Support before use.

Inner Layer

Item	Recommendation
Surface Preparation	Chemical treatment preferred
D.E.S.	Standard process
Oxide	Compatible with most oxide chemicals

CORPORATE HEADQUARTERS

Ventec Electronics Co. Ltd.
308 TaiShan Rd,
New District Suzhou,
Jiangsu, P.R. China 215129
T: +86 512-68091810
Email: sales@ventec.com.cn

EMEA REGIONAL HEADQUARTERS

Ventec Europe
Unit 1 Trojan Business Centre,
Tachbrook Park Estate,
Leamington-Spa, CV34 6RH, UK
T: +44 1926-889822
Email: sales@ventec-europe.com

AMERICAS REGIONAL HEADQUARTERS

Ventec USA
700 Lee St., Elk Grove Village,
Illinois, IL 60007,
United States of America
T: +1 630-4221627
Email: saleseast@ventec-usa.com

VT-4A2H

Laminate/Prepreg

UL Approval: E214381 Version: Preliminary 1

Press Condition

Item	Recommendation
1. Heating rate (Rise of Rate) on Product	3-6°C min (5~10°F/min)
2. Full Pressure on Product	≥400psi in 5~10 minutes after pressing starts
3. Curing Temperature & Time	>50min at more than 170°C (338°F) on Product
4. Vacuuming should be continued until over 140°C (284°F) [Material Temperature]	
5. Cold Press condition: Keep Plate cooled by water; Pressure: 100psi; Dwell: 60 minutes	

Machining & Wet Processes

Item	Recommendation
Drilling	Excessive wear of carbide drill bits. Diamond coated drill
Desmearing	Alkaline permanganate or plasma
Metallization	Compatible with direct deposit or electroless copper processes
Surface Finish	Compatible with OSP, HASL, ENIG, etc. Bake prior to HASL.
Punching & Routing	Aggressive wear of machining tools

CORPORATE HEADQUARTERS

Ventec Electronics Co. Ltd.
308 TaiShan Rd,
New District Suzhou,
Jiangsu, P.R. China 215129
T: +86 512-68091810
Email: sales@ventec.com.cn

EMEA REGIONAL HEADQUARTERS

Ventec Europe
Unit 1 Trojan Business Centre,
Tachbrook Park Estate,
Leamington-Spa, CV34 6RH, UK
T: +44 1926-889822
Email: sales@ventec-europe.com

AMERICAS REGIONAL HEADQUARTERS

Ventec USA
700 Lee St., Elk Grove Village,
Illinois, IL 60007,
United States of America
T: +1 630-4221627
Email: saleseast@ventec-usa.com

www.ventec laminates.com